

Technical data sheet in accordance with ASTM

## Material 70 AU 6865



[CONTACT US](#)

**revision index**

1

**revision date**

3/8/2021

**page**

1 / 2

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D297	---	---	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	---	70	Shore
<b>Modulus</b> 100 %, ASTM D412, C	---	650	Psi
<b>Tensile strength</b> ASTM D412, C	---	5000	Psi
<b>Elongation at Break</b> ASTM D412, C	---	725	%
<b>Compression set</b> ASTM D395, B, 70 h, 70 °C, 25 %	---	12	%

### Declarations of conformity

No data found!

### Freudenberg

Freudenberg FST GmbH  
Global Material Technology  
Daniel Danzer  
Telefon: +49 6201 960 5033  
Fax: -  
Email: Daniel.Danzer@fst.com

Technical data sheet in accordance with ASTM

## **Material**

### **70 AU 6865**

**revision index**

1

**revision date**

3/8/2021

**page**

2 / 2

#### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

#### **Freudenberg**

Freudenberg FST GmbH  
Global Material Technology  
Daniel Danzer  
Telefon: +49 6201 960 5033  
Fax: -  
Email: Daniel.Danzer@fst.com