

Technical data sheet in accordance with ASTM

Material
92 AU 9251

natural



[CONTACT US](#)

revision index
2

revision date
7/7/2020

page 1 / 2

Physical properties	nominal range	typical values	
Density ASTM D297	1.17 ±0.02	1.17	g/cm ³
Hardness ASTM D2240, Shore A	92 ±5	90	Shore
Modulus 100 %, ASTM D412, C	---	1500	Psi
Tensile strength ASTM D412, C	5000	6000	Psi
Elongation at Break ASTM D412, C	---	420	%
Rebound resilience ASTM D2632	---	35	%
Compression set ASTM D395, B, 70 h, 70 °C, 25 %	---	18	%
Compression set ASTM D395, B, 70 h, 100 °C, 25 %	---	33	%
Low Temperature ISO 11357-2, DSC	---	-36	°C
Temperature range	-30°C to 100°C		

Declarations of conformity
No data found!

Technical data sheet in accordance with ASTM

Material
92 AU 9251
natural

revision index
2

revision date
7/7/2020

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 960 5033
Fax: -
Email: Daniel.Danzer@fst.com