

Material

70 EPDM 391

black

cross linking: peroxidic



[CONTACT US](#)

revision index

3

revision date

9/20/2011

page 1 / 2

Physical properties

Density

DIN EN ISO 1183-1, 23 °C

nominal range

typical values

1.04

g/cm³

Hardness

DIN ISO 7619-1, Shore A, 23 °C

72

Shore

Modulus

100 %, DIN 53504, S2, 23 °C

MPa

Tensile strength

DIN 53504, S2, 23 °C

16.8

MPa

Elongation at Break

DIN 53504, S2, 23 °C

151

%

Compression set

DIN ISO 815, B, 24 h, 150 °C, 25 %

13

%

Temperature range

-40°C to 150°C

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
ADI Free					<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
USP Chapter 87 (In vitro)	USA	Seals			<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 960 5033
Fax: -
Email: Daniel.Danzer@fst.com



Material 70 EPDM 391

black

cross linking: peroxidic

revision index

3

revision date

9/20/2011

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 960 5033
Fax: -
Email: Daniel.Danzer@fst.com

