

Material

85 Simriz 496

print date	revision index	revision date	page	1/1
12/8/2014	5	5/2/2013		

Physical properties	required	actual	
Density DIN EN ISO 1183-1, 23 °C	1.84 ±0.03	1.84	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	85 ±5	86	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	---	MPa
Tensile strength DIN 53504, S2, 23 °C	---	17.2	MPa
Elongation at Break DIN 53504, S2, 23 °C	---	77	%
Compression set DIN ISO 815, B, 24 h, 200 °C, 25 %	< 30	23	%

Attention! preliminary data sheet

Temperature-range: - 15 °C to 260 °C (for a short time to max. 300 °C)

explosive decompression in carbon dioxide:

100 °C / 100 bar = OK

30 °C / 100 bar = OK

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

FST - MCE

Material Center EUROPE

Wolfgang Becker

Phone: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com