



COMPOUND DATA SHEET

Parker O-Ring & Engineered Seals Division, North America

MATERIAL REPORT

Report Number: MTR 30962
1/25/2005



[CONTACT US](#)

Title: Evaluation of Parker Compound

Elastomer Type: Fluorocarbon (FKM) V1226-75

Purpose: To obtain typical test data

Specification: ASTM D2000 M4HK710 A1-11 B38 EF31 EO78 Z1 Z2 Z3
Z1 = 75 ± 5 Durometer
Z2 = 150% Minimum Elongation
Z3 = Brown

Color: Brown

Recommended Temperature Range: -15°F to 400°F

Recommended For: Mineral oil and grease, IRM 901, IRM 902, IRM 903, nonflammable hydraulic fluids, silicone oils and greases, aliphatic hydrocarbons (propane, butane, natural gas), aromatic hydrocarbons (benzene, toluene), chlorinated hydrocarbons (trichloroethylene and carbon tetrachloride), gasoline, high vacuum, ozone, weather, and aging

Not Recommended For: Glycol based brake fluids, ammonia gas, amines, alkalis, superheated steam, and low molecular weight organic acids (formic and acetic acid)

Certifications: AMS 7276

*"Purchaser use only. Reproduce only in full. Data pertains to items referenced only.
The recording of false, fictitious, or fraudulent statements or entries in the report may be punishable
as a felony under federal law."*

REPORT DATA

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Results</u>
(Z1) Hardness, Shore A, pts.	ASTM D2240	75±5	78
Tensile Strength, PSI	ASTM D412	1450	2328
(Z2) Ultimate Elongation, %	ASTM D412	150	181
(Z3) Color	-	Brown	Brown
(B38) Compression Set <u>22 hrs. @ 392°F (200°C)</u>	ASTM D395		
% of Original Deflection max.	Method B	50	9
(A1-11) Heat Age <u>70 hrs. @ 527°F (275°C)</u>			
Hardness Change, pts.	ASTM D573	+10	+1
Tensile Strength Change, %		-40	-19
Elongation Change, %		-20	+8
IRM 903 Resistance <u>70 hrs. @ 302°F (150°C)</u>			
Volume Change, %	ASTM D417	+10	+2
(EF31) Fluid Resistance <u>Fuel C, 70 hrs. @ 73°F (23°C)</u>			
Hardness Change, pts.	ASTM D471	±5	-3
Tensile Strength Change, %		-25	-24
Elongation Change, %		-20	-6
Volume Change, %		0 to +10	+2
(EO78) Fluid Resistance <u>Service Fluid 101, 70 hrs. @ 392°F (200°C)</u>			
Hardness Change, pts.	ASTM D471	-15 to +5	+1
Tensile Strength Change, %		-40	-26
Elongation Change, %		-20	-3
Volume Change, %		0 to +15	+4