



MATERIAL REPORT



CONTACT US

REPORT NUMBER:
DATE: 1/29/2002

TITLE: Evaluation of Parker Compound VG162-75 (19727)

PURPOSE: To obtain general information

Recommended temperature limits: -15⁰F to 400⁰F

Recommended For

Fuels

Petroleum, mineral, and vegetable oils

Silicone fluids

Aromatic hydrocarbons (benzene, toluene)

Chlorinated hydrocarbons

High vacuum

Ozone, weather, aging resistance

Not Recommended For

Hot water and steam

Auto and aircraft brake fluids

Amines

Ketones

Low molecular weight esters and ethers



REPORT DATA

	Test Results
Original Physical Properties, ASTM D412, D2240	
Hardness, Shore A, pts.	72
Tensile Strength, psi	1871
Ultimate Elongation, %	209
Compression Set, ASTM D395 Method B (22 hrs. @ 392°F)	
Percent of Original Deflection (plied)	24
Dry Heat Resistance, ASTM D573 (70 hrs. @ 482°F)	
Hardness Change, pts.	+2
Tensile Change, %	-10
Elongation Change, %	-2
Fluid Immersion, ASTM D471 Fuel C, (70 hrs. @ 73°F)	
Hardness Change, pts.	-2
Tensile Change, %	-5
Elongation Change, %	+8
Volume Change, %	+1
Fluid Immersion, ASTM D471 ASTM Service Fluid #101, (70 hrs. @ 392°F)	
Hardness Change, pts.	-4
Tensile Change, %	-9
Elongation Change, %	+9
Volume Change, %	+6
Fluid Immersion, ASTM D471 Methanol, (70 hrs. @ 73°F)	
Volume Change, %	+2