



MATERIAL REPORT



CONTACT US

REPORT NUMBER:
DATE: 8/22/97

TITLE: Evaluation of Parker Compound N1173-70
PURPOSE: To obtain general information.

Recommended temperature limits: -25⁰F to 300/325⁰F

Recommended For

Petroleum based hydraulic oil, motor oil, transmission fluid,
grease
R134a
Water/glycol/steam
HFA, HFB, and HFC fluids
Ozone, aging, and weather resistance

Not Recommended For

Polar solvents (ketones and esters)
Strong acids
Chlorinated hydrocarbons
Auto and aircraft brake fluids



REPORT DATA

Report Number:

	<u>Platen Results</u>
<u>Basic Physical Properties</u>	
Hardness, Shore A	74
Tensile Strength, MPa	22.8
Elongation, %	206
Modulus @ 100%, MPa.	9.1
25% Compressive Modulus, Mpa	4.0
<u>Heat Aging, ASTM D573, 70 H @ 150 °C</u>	
Hardness Change, pts	+3
Tensile Change, %	-4
Elongation Change, %	-18
Surface Condition	No change
<u>Fluid Immersion, ASTM #1 Oil, ASTM D471, 70 H @ 150 °C</u>	
Hardness Change, pts	-1
Tensile Change, %	+11
Elongation Change, %	+10
Volume Change, %	+2.0
<u>Fluid Immersion, IRM 903 Oil, ASTM D471, 70 H @ 150 °C</u>	
Hardness Change, pts	-9
Tensile Change, %	-13
Elongation Change, %	-11
Volume Change, %	+18.5
<u>Fluid Immersion, Diesel #2, ASTM D471, 70 H @ 65 °C</u>	
Hardness Change, pts	-10
Tensile Change, %	-15
Elongation Change, %	-14
Volume Change, %	+28.3